

Abstract

This standard addresses factors that affect weld discoloration on the inside of austenitic stainless steel tube. The document contains a color illustration relating the discoloration to the oxygen content of the backing shielding gas.


Guide to Weld Discoloration Levels on Inside of Austenitic Stainless Steel Tube

1. This standard provides a visual comparison guide that can be used to specify surface discoloration criteria for sanitary (hygienic) welds in austenitic stainless steel tube.

This figure has been extracted from AWS D18.1/D18.1M:2009.

2. **The Tube Sample.** The tube sample was prepared using an automatic orbital “bead-on-plate” weld on the outside diameter of a 2 in [50.8 mm] stainless steel tube. The weld penetrated through the tube wall. The concentration of oxygen in ppm added to the pure argon backing gas for each weld was as follows:

No. 1—10 ppm	No. 3—50 ppm	No. 5—200 ppm	No. 7—1000 ppm	No. 9—12 500 ppm
No. 2—25 ppm	No. 4—100 ppm	No. 6—500 ppm	No. 8—5000 ppm	No. 10—25 000 ppm



Weld Discoloration Levels on Inside of Austenitic Stainless Steel Tube

3. The illustration is most useful as a reference to identify the degree of discoloration rather than to specify oxygen limits in the backing gas. The amount of discoloration and its appearance can be influenced by factors other than oxygen such as:

- High levels of moisture in the backing gas will increase the degree of discoloration.
- Contaminants such as hydrocarbons, moisture, and some types of particulate on the surface prior to welding can influence discoloration levels.
- Hydrogen gas in the argon backing gas can significantly reduce the amount of discoloration.
- The metal's surface finish can affect the appearance of discoloration.

No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.



American Welding Society
550 N.W. LeJeune Road, Miami, FL 33126



Statement on the Use of AWS American National Standard Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 978-0-87171-756-6

American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126

© 2009 by American Welding Society. All rights reserved.

Printed in the United States of America

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While the AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions are entrusted to appropriately qualified and competent personnel.

This standard may be superseded by the issuance of new editions. Users should ensure that they have the latest edition.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

Finally, the AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

On occasion, text, tables, or figures are printed incorrectly, constituting errata. Such errata, when discovered, are posted on the AWS web page (www.aws.org).

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 550 N.W. LeJeune Road, Miami, FL 33126. With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D18 Committee on Welding in Sanitary Applications. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D18 Committee on Welding in Sanitary Applications and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D18 Committee on Welding in Sanitary Applications to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

AWS D18 Committee on Welding in Sanitary Applications

J. E. Campbell, Chair	<i>WeldTech Solutions Corporation</i>
W. L. Roth, 1st Vice Chair	<i>Procter & Gamble, Incorporated</i>
R. Howard, 2nd Vice Chair	<i>Vogt Power International</i>
R. Starks, Secretary	<i>American Welding Society</i>
R. E. Avery	<i>Nickel Institute</i>
R. D. Campbell	<i>Bechtel National, Incorporated</i>
L. Hanson	<i>Johnsonville Sausage, LLC</i>
B. K. Henon	<i>Arc Machines Incorporated</i>
E. K. Johnson	<i>SWECO Division of M-I LLC</i>
J. McSwiggin	<i>Rodem, Incorporated</i>
J. Williams	<i>James Williams, PC</i>

Advisors to the AWS D18 Committee on Welding in Sanitary Applications

L. P. Connor	<i>Consultant</i>
J. R. Hannahs	<i>Professor</i>
M. P. Lang	<i>United Association Local 501</i>
G. B. Melton	<i>TWI</i>
J. R. Miller	<i>Retired</i>
R. K. Smith	<i>Richard K. Smith</i>